Primary lithium battery

LS 14250

3.6 V Primary lithium-thionyl chloride (Li-SOCl₂) High energy density ½AA-size bobbin cell



Benefits

- High voltage, stable during most of the application's lifetime
- Wide operating temperature range
- Low self-discharge rate (less than 1 % per year of storage at +20°C)
- Easy integration into compact systems
- Superior resistance to atmospheric corrosion

Key features

- Stainless steel container and end caps (low magnetic signature)
- Hermetic glass-to-metal sealing
- Non-flammable electrolyte
- Compliant with IEC 86-4 safety standard and EN 50020 intrinsic safety standard
- Underwriters Laboratories (UL)
 Component Recognition
 (File Number MH 12609)
- Non-restricted for transport

Main applications

- Utility metering
- Automatic meter reading
- Alarms and security devices
- Memory back-up
- Computer real-time clocks
- Tracking systems
- Automotive electronics
- Professional electronics

Cell Size references /2 NO - /2 AA	Cell size references	½ R6 – ½ AA
------------------------------------	----------------------	---------------------------

Electrical characteristics

(typical values relative	to cells stored for one year or less at $+30^{\circ}\text{C}$ max.)			
Nominal capacity		1.20 Ah		
(at 1 mA + 20° C 2.0 V cut-off. The capacity restored by the cell varies according to current drain, temperature and cut-off)				
Open circuit voltage	(at + 20°C)	3.67 V		
Nominal voltage	(at 0.1 mA + 20°C)	3.6 V		

Pulse capability: Typically up to 100 mA (100 mA/0.1 second pulses, drained every 2 mn at $+20^{\circ}\mathrm{C}$ from undischarged cells with 10 $\mu\mathrm{A}$ base current, yield voltage readings above 3.0 V. The readings may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult Saft)

	nmended continuous current s are possible, consult Saft)	35 mA
Storage	(recommended) (for more severe conditions, consult Saft)	+ 30°C (+ 86°F) max
Operating temperature range		-60°C/+85°C
(Operation above ambient T may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult Saft)		(-76°F/+185°F)

Physical characteristics


Diameter (max)	14.65 mm (0.58 in)
Height (max)	24.8 mm (0.98 in)
Typical weight	8.9 g (0.3 oz)
Li metal content	approx. 0.3 g

Available termination suffix

CN, CNR radial tabs
2 PF, 3 PF, 3 PF RP, 4 PF radial pins
CNA (AX) axial leads
FL flying leads ...etc.



LS 14250



Dimensions in mm.


3.6 3.5 3.4 2 3.3 3.2 3.1 3.0 2.9 2.8 2.7 2.6

Current (mA)

10

100

Voltage plateau versus Current and Temperature (at mid-discharge)




Storage

 The storage area should be clean, cool (preferably not exceeding + 30°C), dry and ventilated.

Warning

- Fire, explosion and burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above 100°C (212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell (use tabbed cell versions instead).

Restored Capacity versus Current and Temperature (2.0 V cut-off)



Saft Specialty Battery Group12, rue Sadi Carnot

93170 Bagnolet - France Tel.: +33 (0)1 49 93 19 18 Fax: +33 (0)1 49 93 19 69

www.saftbatteries.com

Doc. N° 31072-2-0308

Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft. For more details on primary lithium technologies please refer to Primary Lithium Batteries Selector Guide Doc N° 31048-2.

Published by the Communications Department

Photo credit: Saft

2.5

0.01

0.1

Société anonyme au capital de 31 944 000 €

RCS Bobigny B 383 703 873

Produced by Arthur Associates Limited.

